



(11) **EP 0 914 933 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
 12.05.1999 Bulletin 1999/19

(51) Int. Cl.⁶: **B29C 55/14, B29D 28/00**

(21) Application number: **97830567.0**

(22) Date of filing: **04.11.1997**

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE
 Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Baretta Mario**
23896 Sirtori (IT)


(74) Representative:
Modiano, Guido, Dr.-Ing. et al
Modiano & Associati SpA
Via Meravigli, 16
20123 Milano (IT)

(71) Applicant: **Tenax S.p.A.**
22060 Vigano (Lecco) (IT)

(54) **Method for stretching plastic nets and grids and apparatus for performing the method**

(57) The present invention relates to a method for stretching plastic nets (3) and grids (5), which has the particularity that it consists in subjecting the product to be stretched (3, 5) to irradiation with electromagnetic waves with a wavelength above the infrared range (11, 12, 20 and 30), so as to heat the product by dielectric

loss, and in subjecting the product to traction in order to produce stretching in at least one direction. The method allows to substantially improve the ability of the polymer to absorb the energy in order to profitably perform the stretching process.



EP 0 914 933 A1

Description

[0001] The present invention relates to a method for stretching plastic nets and to the apparatus for performing the method.

[0002] The expression "stretching method" designates the modification, by mechanical action (stretching), of the morphological structure of a polymeric material in order to obtain a specific performance, such as an increase in pulling strength and in the elasticity modulus of the product and a decrease in breaking elongation.

[0003] In order to perform the stretching method the material is conventionally first heated, directly raising the temperature of its outer surface and then gradually increasing the temperature of its inner layers by conduction.

[0004] Systems based on water, air, hot rollers and infrared radiation are used to perform heating. In particular, all currently known stretching systems utilize the principle of heat conductivity to transfer heat from the outer layers to the inner layers of the product.

[0005] Accordingly, it is necessary to produce a difference in temperature between the inner layer and the outer layer in order to produce heat exchange and a certain variable amount of time is required to provide a uniform distribution of the temperature inside the material, in order to obtain the intended thermal conditions.

[0006] Conventional systems entail the drawback that they frequently damage the surface of the products subjected to high temperature for a certain time, i.e., for the time required to make the heat uniformly penetrate the inner layers.

[0007] The temperature difference between the inner and outer layers causes creep in the overheated outer layers and cracks and fissures in the insufficiently heated inner layers.

[0008] Another drawback is also constituted by the intense internal stresses in the presence of sharp temperature gradients caused by the difference in temperature between the outer and inner layers both during heating and during cooling.

[0009] These stresses cause breakages or less than optimum alignments during stretching; accordingly, the finished product can be affected by the damage caused by the systems currently being used and can have undesirable cracks, brittleness, elongations and discontinuities.

[0010] Another drawback arising from the use of conventional systems is the large amount of energy required to heat plastic materials with current conduction systems, which often entail problems in dissipating the heat in the heat-producing means.

[0011] The above-mentioned drawbacks worsen as the thickness of the material to be heated increases and as the differences in thickness of the cross-sections of the product increase.

[0012] Temperature adjustment in conventional

stretching systems also does not allow precise and immediate variations in the temperature of the product to be stretched, owing to the thermal inertia that is typical of the heating system used so far.

[0013] Another drawback is also caused by the fact that in order to efficiently vary the temperature of the entire product it is necessary to vary the temperature of the heating means, which in turn propagates, with its specific inertia, the variation to the surface of the net.

[0014] In order to try to improve stretching conditions, in conventional systems the materials are stretched substantially during the heating of the net, since the degree of dissipation of the superficially absorbed heat is high.

[0015] In conventional systems, energy utilization is not strictly proportional to the amount of polymer to be heated, since in any case it is necessary to bring, and keep, the space wherein stretching is performed to a temperature such that the conduction process transfers a sufficient amount of heat to the innermost layers.

[0016] Conventional stretching systems have the limitation that it is necessary to adapt the stretching speed to the mass of product to be stretched, since the temperature of the heating means cannot be raised further without severely damaging the net, unless resorting to expensive contrivances which increase the heat exposure time by extending the space traveled inside the heating means.

[0017] Water-based heating also entails the need to dry the product and to continuously replace the amount of water that has evaporated and been removed.

[0018] Air-based heating entails using large amounts of power in order to keep the temperature constant, so as to contrast thermal dissipations; this system also forces stretching of plastic materials at low speed in order to allow a uniform and useful heat conduction effect, consequently reducing productivity.

[0019] Heating with metal rollers which are internally heated by means of diathermic oil entails the problem of poor heat transmissivity, which worsens in uneven materials wherein contact is limited only to the protruding surfaces; uneven heat propagation also causes drawbacks during stretching and consequent defects in the final product.

[0020] Heating by infrared radiation has the drawback that it directly heats only the surface layer of the material and does not produce uniform heating per unit mass; infrared radiation also entails the drawback that it is ionizing and as such is dangerous to the operator.

[0021] Examples of stretching obtained with conventional heating systems are disclosed in US-4,152,479 and in GB-2035191, GB-2073090 and GB-135901.

[0022] Plastic materials have already been subjected, in other applications, to heating by means of electromagnetic waves and more particularly radio frequency waves or microwaves. Many plastics, differently from those used in the present invention, are in fact classified as dielectric materials which have the property that they

become polarized because their structure has strong electron bonds. Accordingly, when they are placed in an electromagnetic field which varies with radio frequencies or microwave frequencies, plastic materials such as PET, POM and others undergo continuous polarization changes which can increase the temperature of the material.

[0023] Examples of teachings related to these applications arise from JP-6246619 and JP-60220730. Differently from the present invention, these patents do not provide for the heating of polyolefins, which constitute the base polymers used by the present invention. These inventions also use a heating step performed with conventional means, which as mentioned can cause the above-cited drawbacks.

[0024] It is also currently known to stretch, with heating, by dielectric loss, only strands or films of polyethylene characterized by very low thicknesses and by a uniform and constant thickness (JP-60173114 and JP-57193513).

[0025] The thicknesses, the lack of regions that interconnect the strands and the constant thickness and cross-section deeply differentiate the state of the art from the present invention.

[0026] Finally, the materials employed in the present invention, namely polyolefins, were hitherto substantially not capable of being heated by dielectric loss.

[0027] Since the ability to heat up is in fact linked to a coefficient, known as loss factor, it can be seen that for polyethylene said factor is between 0.001 and 0.0004, while it is between 0.003 and 0.014 for polypropylene, showing an almost nil heating ability; indeed, these materials are applied inside radiofrequency microwave ovens as supports which indeed do not heat up.

[0028] The aim of the present invention is to eliminate the drawbacks mentioned above in conventional hot-stretching methods by providing a method in which it is possible to heat a plastic product uniformly and simultaneously in all the layers of its mass.

[0029] Within the scope of this aim, a particular object of the invention is to provide a method which allows to achieve optimum stretching in all the layers of the mass that forms the plastic material and particularly to subject the macromolecules to uniform alignment along the stretching direction, since the difference in temperature between the layers is eliminated, the temperature gradient is eliminated, and the formation of cracks in the inner layers and of creep deformations in the outer layers is prevented, also because the tensions inside the material, caused by thermal gradients, and breakages by shearing of the inner parts of the plastic product are decreased together with dimensional nonuniformities caused by uneven heating.

[0030] Another object of the present invention is to provide a method in which thermal transients, i.e., the time required to vary the temperature inside the product, are reduced drastically, with the advantage of being able to provide a substantially instantaneous leveling of

the intended temperature and to keep it at the set value during stretching.

[0031] This aim, these objects and others which will become apparent hereinafter are achieved by a method for stretching plastic nets, characterized in that it consists in subjecting the product to be stretched to irradiation with electromagnetic waves with a wavelength above the infrared range, so as to heat said product by dielectric loss, and in subjecting the product to traction in order to produce stretching in at least one direction.

[0032] Further characteristics and advantages of the present invention will become apparent from the description of a preferred but not exclusive embodiment of a method and an apparatus for stretching plastic nets, illustrated in the accompanying figures, wherein:

figure 1 is a schematic view of the longitudinal stretching of a plastic net which is heated by passing through a cavity that contains microwaves;

figure 2 is a schematic view of a machine for in-line longitudinal and transverse stretching;

figure 3 is a schematic view of an example of application of a microwave source to a stretching process;

figure 4 is a schematic view of an example of application of a radiofrequency source to a stretching process.

[0033] First of all, it should be noted that in order to perform the dielectric-loss stretching method it has been observed that it is necessary to use a polymeric material whose loss factor is not less than 0.01.

[0034] Having found that polyolefins (PP and PE), of which the grid-like material used for nets and geotechnical products are normally made, are not sensitive to irradiation with electromagnetic waves and do not undergo a temperature increase which is adapted to perform stretching, the present invention seeks to allow stretching with heating by dielectric loss even in these materials.

[0035] It has been found experimentally that in order to achieve heating by dielectric loss with polyolefins and the like it is necessary to add additives to the polyolefin base mix in order to achieve a degree of absorption of the energy carried by magnetic waves at radio and microwave frequencies such that the material undergoes a uniform heating which is sufficient for the correct execution of the stretching method.

[0036] The kind of additive to be used in order to allow stretching is one capable of increasing the loss factor to a value of at least 0.01; the additive is added in a percentage between 1 and 30% of the mix.

[0037] It has been found experimentally that graphite or carbon black and other semiconductors such as silicon, materials with polar molecular structures such as phenol-formaldehyde, PVC, polyamides and cellulose esters, are effective additives.

[0038] Carbon black or graphite, added in a percent-

age between 3% and 20%, have been found to be ideal.

[0039] Experimentally, a 1200 nominal watt microwave oven was used inside which 300 g of product, obtained from a mix formed by polypropylene with the addition of approximately 5% graphite or carbon black at the temperature of 21°C, was introduced.

[0040] The oven was set to maximum power for approximately 70 seconds and at the end of the cycle it was noted that the temperature of the product, regardless of its shape, was approximately 80°C as a whole; this temperature is ideal for stretching.

[0041] The type of microwave, as shown in figure 1, provides for the introduction of energy- and direction-modulated microwaves inside a coil 1 by means of the iris diaphragm 2, which provides uniform irradiation on the net 3 that passes through the coil 1, uniformly irradiating said grid.

[0042] The net 3, struck by the electromagnetic wave, absorbs its energy, undergoing a uniform and simultaneous increase in temperature in all its layers and causing a gradual loosening of the molecules.

[0043] The net 3, at room temperature, passes through the coil 1 and, after undergoing heating by dielectric loss, stretches uniformly in the strand and in the node, according to the pulling speed set by the rollers 4.

[0044] Figure 2 illustrates an apparatus for stretching a plastic grid 5, which has a first station 11 and a second station 12 which produce high-frequency heating, combined with an apparatus which performs preliminary longitudinal stretching and then performs stretching transversely to the grid 5.

[0045] The non-oriented net 3 is passed inside the oven 11, where a high-frequency electric field is provided, in the radio frequency or microwave range, and longitudinal stretching is performed at the exit in order to introduce the product in a second high-frequency heating station, at the outlet whereof the product is subjected to stretching in a transverse direction.

[0046] Figure 3 illustrates a microwave source, generally designated by the reference numeral 20, which irradiates the net 3, which is subjected to stretching by means of traction rollers 21.

[0047] Likewise, figure 4 illustrates a radiofrequency oven, designated by the reference numeral 30, which uniformly irradiates the material that is passed inside it.

[0048] The above-described invention is based on introducing the grid-like material in a radio- or microwave-frequency variable electric field, in which heat is generated inside the mass of strands and nodes by rapid reversal of the polarization of the individual molecules.

[0049] Surprisingly, the temperature rises uniformly and simultaneously throughout the net, regardless of the existing thickness variation, so that the heating that is performed allows to achieve, in the irradiated regions, optimum stretching in all the layers of the strands and nodes, since the macromolecules undergo uniform and simultaneous elongation in the stretching direction.

[0050] The advantages of the present invention are particularly evident in the case of semirigid components having considerable thickness variations which mainly occur in the strand connecting regions.

[0051] The possibility of achieving uniform heating prevents molecular orientation from occurring first in the thinner regions and then advancing towards the thicker ones and instead allows it to occur simultaneously in all the regions, and the molecules, subjected to stretching, begin to orient themselves simultaneously.

[0052] Accordingly, a uniform and optimum molecular orientation is obtained, which avoids the occurrence of breakages in the region where the strands and the node mutually connect during stretching.

[0053] The possibility to achieve optimum temperature distribution allows to control one of the fundamental parameters of stretching and of the net, greatly minimizing the risk of weakening the node and of webbing, as disclosed for example in IT-867426.

[0054] The kind of heating according to the invention therefore eliminates the difference in temperature among layers, indeed in the presence of those differences in cross-section and thickness that currently cause several problems, and the temperature gradient and the formation of cracks in the inner layers and of creep deformation in the outer layers are eliminated.

[0055] The uniform heating of the entire mass of the net also provides the advantage of eliminating the tensions inside the material caused by thermal gradients, which are otherwise inevitable with conventional heating systems, which can cause unwanted weakenings of the structure of the net.

[0056] During stretching, breakages by shearing of the internal parts of the plastic net and size irregularities caused by uneven elongation are no longer found.

[0057] Heating by dielectric loss allows to drastically reduce thermal transients, i.e., the period of time required to vary the temperature inside the net, providing a substantially instantaneous adjustment of the intended temperature and the possibility to maintain the set value during stretching.

[0058] The extreme precision in the adjustment of the energy transmitted to the net and the possibility of an irradiation which is optionally localized to single parts or sections advantageously allows to perform stretching even for net portions, leaving the remaining portions substantially not oriented.

[0059] The flexibility of the system allows to stretch plastic nets at uniform or modulated intervals, according to the required stretching criteria.

[0060] Another advantage arising from the invention is the possibility to eliminate the time and cost required to heat the conventional heating means (water, air, heated metal rollers), since system startup times are entirely eliminated, providing a considerable energy saving and a reduction in production times, with the possibility to stretch the net at the same time as system startup.

[0061] The present invention also allows to effectively

perform stretching both during heat irradiation and during a subsequent step, since the energy accumulated as heat in the innermost layers ensures the persistence of the stretching conditions, especially in the thicker regions, such as the node, where cooling is slow and gradual from the outermost layers to the innermost ones.

[0062] The invention also eliminates one of the severe drawbacks that can occur when stretching is halted due to unexpected events during production, namely net overheating.

[0063] The possibility to adjust and deactivate the delivery of energy and the consequent interruption of the application of heat eliminates the risk of overheating and damage to the plastic net.

[0064] Another advantage of the present invention also resides in the fact that it is possible to perform stretching in less space and in a shorter time for an equal mass.

[0065] Stretching operations can be performed at a higher stretching speed than allowed by conventional systems, since it is possible to uniformly introduce into the net the heat required for stretching, over a period of time which is set according to the requirements of the operator, modulating proportionally the amount of energy to be applied.

[0066] The novelty is also introduced, with respect to conventional stretching methods, to perform stretching in a small space in order to provide molecular orientation; the molecules, if heated appropriately and uniformly, are in fact capable of undergoing a high stretch ratio inside a compact stretching machine without subjecting the product to unwanted shearing or tearing due to the sudden and intense traction.

[0067] The stretching rate can be increased conveniently as a function of the mass of the net but independently of thickness variations along the net, since it is a function of the amount of energy to be irradiated.

[0068] The short time during which stretching is performed advantageously allows to achieve a considerable increase in plant productivity, with an energy consumption which is proportional to the mass of product to be stretched and to the production rate that the operator intends to use.

[0069] By way of example, it should be noted that just 100 kW of installed power allow to double the productivity of a hot-air transverse stretching machine which is 50 m long.

[0070] By producing a substantially uniform heating inside the mass, advantages are obtained which increase as the variation in the cross-section of the net increases, as the thickness of the net increase, and as the thickness variations along the net increase.

[0071] Drastic reductions in the manufacturing and maintenance costs of stretching systems are also achieved by virtue of their size, the reduced complexity of ancillary equipment and the lower thermal stresses to which the entire equipment is subjected.

[0072] The invention thus conceived is susceptible of numerous modifications and variations, all of which are within the scope of the inventive concept.

[0073] All the details may also be any according to requirements.

[0074] In practice, the materials employed, so long as they are compatible with the specific use, as well as the contingent shapes and dimensions, may be any according to requirements.

[0075] Where technical features mentioned in any claim are followed by reference signs, those reference signs have been included for the sole purpose of increasing the intelligibility of the claims and accordingly such reference signs do not have any limiting effect on the interpretation of each element identified by way of example by such reference signs.

Claims



1. A method for stretching plastic nets or grids, characterized in that it consists in subjecting the product to be stretched to irradiation with electromagnetic waves with a wavelength above the infrared range, so as to heat said product by dielectric loss, and in subjecting the product to traction in order to produce stretching in at least one direction.
2. A method according to claim 1, characterized in that it irradiates by using microwave-type electromagnetic waves.
3. A method according to the preceding claims, characterized in that it irradiates by using radiofrequency electromagnetic waves.
4. A method according to the preceding claims, characterized in that the plastic material that constitutes the product to be stretched has a loss factor of more than 0.01.
5. A method according to one or more of the preceding claims, characterized in that it consists in adding additives to the polyolefin base mix in order to produce, in the polymeric material, a loss factor of more than 0.01.
6. A method according to one or more of the preceding claims, characterized in that said additives are comprised in a percentage between 1 and 30%.
7. A method according to one or more of the preceding claims, characterized in that said additives are constituted by graphite or carbon black.
8. A method according to one or more of the preceding claims, characterized in that said additives are constituted by semiconductors.

9. A method according to one or more of the preceding claims, characterized in that said semiconductors are constituted by silicon.
10. A method according to one or more of the preceding claims, characterized in that said additives are constituted by materials having polar molecular structures. 5
11. A method according to one or more of the preceding claims, characterized in that said polar molecular structures are constituted by phenol-formaldehyde. 10
12. A method according to one or more of the preceding claims, characterized in that said polar molecular structures are constituted by PVC. 15
13. A method according to one or more of the preceding claims, characterized in that said polar molecular structures are constituted by cellulose esters and polyamides. 20
14. A method according to one or more of the preceding claims, characterized in that it performs the heating of discrete portions of said product in order to stretch said described portions without orienting the remaining portions. 25
15. An apparatus for performing the method according to the preceding claims, characterized in that it comprises a coil through which the product to be stretched is passed, energy- and direction-modulated microwaves being injected in said coil. 30
16. An apparatus according to one or more of the preceding claims, characterized in that it comprises a first microwave or radiofrequency oven, downstream of which a longitudinal stretching unit is provided, and a second microwave or radiofrequency oven, downstream of which a transverse stretching unit is provided. 35 40

45

50

55






Fig. 3




Fig. 4

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 83 0567

| DOCUMENTS CONSIDERED TO BE RELEVANT | | | |
|---|--|---|--|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int.Cl.6) |
| Y | PATENT ABSTRACTS OF JAPAN vol. 012, no. 027 (M-662), 27 January 1988 & JP 62 181123 A (NIPPON TELEGR & TELEPH CORP), 8 August 1987. * abstract * | 1-8 | B29C55/14 B29D28/00 |
| A | --- | 15 | |
| Y | FR 2 646 124 A (HUREAU JACQUES) * page 4, line 30 - line 35 * * page 5, line 22 - page 6, line 25 * | 1-8 | |
| Y | US 5 259 097 A (AIHARA KINTARO ET AL) * column 1, line 5 - line 9 * * column 1, line 61 - line 66 * | 1-8 | |
| A | --- | 7 | |
| | DATABASE WPI Section Ch. Week 8925 Derwent Publications Ltd., London, GB; Class A97, AN 89-184051 XP002060142 & JP 01 123 917 A (NIPPON OIL SEAL IND CO LTD), 16 May 1989 * abstract * | | TECHNICAL FIELDS SEARCHED (Int.Cl.6) |
| A | --- | 8 | B29C B29D |
| | DATABASE WPI Section Ch. Week 7930 Derwent Publications Ltd., London, GB; Class A17, AN 79-551298 XP002060143 & JP 54 073 841 A (FURUKAWA ELECTRIC CO LTD), 13 June 1979 * abstract * | | |
| A | --- | 14 | |
| | EP 0 113 203 A (MOBIL OIL CORP) * page 3, line 24 - page 4, line 10 * --- -/-- | | |
| The present search report has been drawn up for all claims | | | |
| Place of search | | Date of completion of the search | Examiner |
| THE HAGUE | | 25 March 1998 | Attalla, G |
| CATEGORY OF CITED DOCUMENTS | | | |
| X particularly relevant if taken alone Y particularly relevant if combined with another document of the same category A technological background C non-written disclosure P intermediate document | | T theory or principle underlying the invention E earlier patent document, but published on or after the filing date D document cited in the application L document cited for other reasons & member of the same patent family, corresponding document | |

EPO FORM 150 (3-92) (P4/C25)

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 83 0567

| DOCUMENTS CONSIDERED TO BE RELEVANT | | |
|---|--|--|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim |
| A | PATENT ABSTRACTS OF JAPAN vol. 010, no. 047 (M-456), 25 February 1986 & JP 60 198211 A (TOYO BOSEKI KK:OTHERS: 01), 7 October 1985, * abstract * ----- | 1 |
| | | CLASSIFICATION OF THE APPLICATION (Int.Cl.6) |
| | | TECHNICAL FIELDS SEARCHED (Int.Cl.6) |
| The present search report has been drawn up for all claims | | |
| Place of search | Date of completion of the search | Examiner |
| THE HAGUE | 25 March 1998 | Attalla, G |
| <p>CATEGORY OF CITED DOCUMENTS</p> <p>X particularly relevant if taken alone Y particularly relevant if combined with another document of the same category A technological background O non-written disclosure P intermediate document</p> <p>T theory or principle underlying the invention E earlier patent document, but published on, or after the filing date D document cited in the application L document cited for other reasons & member of the same patent family, corresponding document</p> | | |

EPO FORM 1503 (3-96) (P4/C11)